

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6 : C09K 11/59, 11/55, 11/71	A1	(11) International Publication Number: WO 99/50371 (43) International Publication Date: 7 October 1999 (07.10.99)
(21) International Application Number: PCT/US99/07080 (22) International Filing Date: 31 March 1999 (31.03.99) (30) Priority Data: 60/079,959 31 March 1998 (31.03.98) US 09/259,661 26 February 1999 (26.02.99) US (71) Applicant: SARNOFF CORPORATION [US/US]; 201 Washington Road, CN5300, Princeton, NJ 08543 (US). (72) Inventor: YOCOM, Perry, Niel; 307 Shadybrook Lane, Princeton, NJ 08540 (US). (74) Agents: BURKE, William, J. et al.; Sarnoff Corporation, 201 Washington Road, CN5300, Princeton, NJ 08543 (US).		(81) Designated States: CN, JP, KR, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: LONG PERSISTENCE RED PHOSPHORS (57) Abstract Long persistence red phosphors of alkaline earth metal phosphates, alkaline earth magnesium silicates and alkaline earth magnesium di-silicates are doubly activated with europium and manganese and contain a trivalent or quadrivalent thermal trapping agent. The thermal trapping cation feeds thermal energy to the europium ion which in turn feeds the energy to the manganese ion that emits in the red region of the spectrum.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MY	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

LONG PERSISTENCE RED PHOSPHORS

This application claims the benefit of Provisional application Serial No. 60/079,958 filed March 31, 1998.

This invention relates to long persistence red emitting phosphors. More particularly, this invention relates to strontium, barium, calcium or magnesium silicates and phosphates that are activated with both europium and manganese and include a trivalent or a quadrivalent rare earth cation.

BACKGROUND OF THE INVENTION

Long persistent red phosphors have been difficult to achieve. Alkaline earth sulfides such as SrS and $(\text{Zn}, \text{Cd})\text{S}:\text{Cu}$ are known. Lindmayer et al in US Patent 5,043,096 disclose that sulfides activated with lanthanum, europium and cerium are red-emitting phosphors; however, they are readily decomposed when exposed to moisture. Further they are fluxed with oxides and a halide such as LiF . The fired phosphor was highly sintered and had to be ground to obtain a useful material. However, grinding degrades the emission, and even heating the ground phosphor did not fully restore its emission.

Royce et al, US Patent 5,650,094, disclose red phosphors of $(\text{Ca}, \text{Pr}, \text{M})$ titanates, wherein M is Zn and/or Mn. Although described as long emitting phosphors, the emission lasts only about 10 minutes.

The only way of obtaining long persistence red emitting materials that has been achieved so far is by filtering green

emitting phosphors, such as Zn:Cu:(Co,Sr) or alkaline earth aluminates activated with europium and dysprosium. However, this method results in a decreased emission intensity.

Thus a search for long persistence, red emitting phosphors has continued.

SUMMARY OF THE INVENTION

The present red emitting, long persistent phosphors are based on incorporating a trivalent or quadrivalent cation that traps thermal energy and provides energy transfer to a divalent europium activator. This energy in turn is fed to a divalent manganese activator, which emits in the red spectral region. Suitable trivalent cations include dysprosium or neodymium; suitable quadrivalent cations include titanium or zirconium. Suitable phosphors of the invention are strontium phosphate, alkaline earth magnesium silicates or alkaline earth magnesium di-silicates doubly activated with europium and manganese and including a suitable trivalent or quadrivalent rare earth trapping cation.

DETAILED DESCRIPTION OF THE INVENTION

The environmentally stable, long persistence red phosphors of the invention operate by energy transfer from a trivalent or quadrivalent trap in the host phosphor material, such as dysprosium, neodymium, zirconium or titanium, which slowly feeds the divalent activator europium and in turn transfers energy to divalent manganese, which emits in the red.

Suitable host phosphors include $\text{Sr}_2\text{P}_2\text{O}_7:\text{Eu:Mn:Dy}$;

$\text{Ba}_3\text{MgSi}_2\text{O}_8\text{:Eu:Mn:Dy}$; $(\text{Ba},\text{Sr},\text{Ca})_3\text{MgSi}_2\text{O}_8\text{:Eu:Mn:Nd}$; and $(\text{Sr},\text{Ba})\text{MgSiO}_4\text{:Eu:Mn:Dy}$.

A suitable concentration of divalent europium is in the range of about 0.1 to 5.0 atom percent; that of divalent manganese is in the range of about 1 to 10 atom percent; and a suitable concentration of the trivalent or quadrivalent rare earths, such as dysprosium, neodymium, titanium or zirconium, is in the range of about 1 to 5 atom percent.

The trivalent or quadrivalent rare earth cation created trap slowly thermally empties, transferring its energy to light energy in the phosphor material. The result is a very long persistent red phosphor that can be used for various safety and decorative uses.

Red phosphors are highly desirable for safety signs in the event of a power failure, such as for "EXIT" signs, and other safety equipment such as fire extinguishers, fire axes, etc. In addition, novelty uses such as for toys, automobile hub caps, sporting goods and clothing are highly desirable because red is a pleasing color.

The phosphors can be made by firing the respective oxides or carbonates in their desired proportion, conveniently in a chloride and/or borate flux.

For example, a merwinite type silicate shows the desired energy transfer to obtain the desired red emission.

As an example, the following oxides and carbonates are mixed together; 42.22 parts by weight of SrCO_3 ; 4.0 parts by weight of MgO ; 12.0 parts by weight of silica; 0.71 part by

weight of Eu_2O_3 ; and 3.4 parts by weight of MnCO_3 . Ammonium chloride (2.3 parts by weight) is added to serve as a flux, and the mixture is fired in an atmosphere of forming gas at a temperature range of about 1100 to 1300°C. The fired material is crushed and the flux removed by washing with water. The resultant compound has the formula $\text{Sr}_{2.86}\text{Eu}_{0.04}\text{Mn}_{0.10}\text{MgSi}_2\text{O}_8$.

A material which forms a trapping site is then added, such as one that includes a trivalent cation or a quadrivalent cation, to provide long persistence emission in the phosphor. Suitable trivalent rare earth cations include dysprosium (Dy) or neodymium (Nd). Suitable quadrivalent cations include zirconium (Zr) or titanium (Ti). The cationic additives are added in amounts of from about 0.1 to 4.0 atomic percent.

Alternatively, or in addition to the ammonium chloride flux, a flux of boron oxide can be used. This flux is conveniently added to the firing mixture in the form of boric acid.

Although the invention has been discussed in terms of specific embodiments, one skilled in the art will be aware of suitable alternative additives and methods of preparation. These are meant to be included herein and the invention is to be limited only by the scope of the appended claims.

I Claim:

1. A long persistence red emitting phosphor comprising a trivalent or quadrivalent ion that acts as a thermal trap in a phosphor comprising a doubly activated alkaline earth phosphate, an alkaline earth magnesium silicate or an alkaline

earth magnesium di-silicate activated with europium and manganese.

2. A phosphor according to claim 1 wherein said trivalent ion is dysprosium.
3. A phosphor according to claim 1 wherein said trivalent ion is neodymium.
4. A phosphor according to claim 1 wherein said quadrivalent ion is titanium.
5. A phosphor according to claim 1 wherein said quadrivalent ion is zirconium.
6. A phosphor according to claim 1 wherein said phosphor is selected from the group consisting of $\text{Sr}_2\text{P}_2\text{O}_7$; Eu:Mn:Dy; $\text{Ba}_3\text{MgSi}_2\text{O}_8$:Eu:Mn:Dy; $(\text{Ba}, \text{Sr}, \text{Ca})_3\text{MgSi}_2\text{O}_8$:Eu:Mn:Nd and $(\text{Sr}, \text{Ba})\text{MgSiO}_4$:Eu:Mn:Dy.
7. A red emitting long persistence phosphor comprising $\text{Sr}_{2.86}\text{Eu}_{0.04}\text{Mn}_{0.10}\text{MgSi}_2\text{O}_8$ activated with a trivalent cation or a quadrivalent cation.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US99/07080

A. CLASSIFICATION OF SUBJECT MATTER IPC(6) : C09K 11/59, 11/55, 11/71 US CL : 252/301.4P, 301.4F According to International Patent Classification (IPC) or to both national classification and IPC																				
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) U.S. : 252/301.4P, 301.4F Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched Electronic data base consulted during the international search (name of data base and, where practicable, search terms used) Please See Extra Sheet.																				
C. DOCUMENTS CONSIDERED TO BE RELEVANT																				
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.																		
X	Chemical Abstract citation 80:102,210; abstract for Japanese B4 patent JP48034115, published 10/18/73.	1 and 5																		
X	US 3,882,041 A (ROYCE) 06 May 1975, col. 1, lines 30-40.	1																		
X	US 5,367,176 A (LEBLANS et al) 22 November 1994, col. 2, lines 25-40.	1 and 5																		
<input type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.																				
<table border="0"> <tr> <td>* Special categories of cited documents:</td> <td>*T*</td> <td>later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</td> </tr> <tr> <td>*A* document defining the general state of the art which is not considered to be of particular relevance</td> <td>*X*</td> <td>document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</td> </tr> <tr> <td>*B* earlier document published on or after the international filing date</td> <td>*Y*</td> <td>document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</td> </tr> <tr> <td>*L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</td> <td>*A*</td> <td>document member of the same patent family</td> </tr> <tr> <td>*O* document referring to an oral disclosure, use, exhibition or other means</td> <td></td> <td></td> </tr> <tr> <td>*P* document published prior to the international filing date but later than the priority date claimed</td> <td></td> <td></td> </tr> </table>			* Special categories of cited documents:	*T*	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention	*A* document defining the general state of the art which is not considered to be of particular relevance	*X*	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone	*B* earlier document published on or after the international filing date	*Y*	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art	*L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*A*	document member of the same patent family	*O* document referring to an oral disclosure, use, exhibition or other means			*P* document published prior to the international filing date but later than the priority date claimed		
* Special categories of cited documents:	*T*	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention																		
A document defining the general state of the art which is not considered to be of particular relevance	*X*	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone																		
B earlier document published on or after the international filing date	*Y*	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art																		
L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*A*	document member of the same patent family																		
O document referring to an oral disclosure, use, exhibition or other means																				
P document published prior to the international filing date but later than the priority date claimed																				
Date of the actual completion of the international search 09 JUNE 1999		Date of mailing of the international search report 24 JUN 1999																		
Name and mailing address of the ISA/US Commissioner of Patents and Trademarks Box PCT Washington, D.C. 20231 Facsimile No. (703) 305-3230		Authorized officer C. MELISSA KOSLOW Telephone No. (703) 308-0661																		

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US99/07080

B. FIELDS SEARCHED

Electronic data bases consulted (Name of data base and where practicable terms used):

CAS ONLINE

search terms: pyrophosphate#, phosphate#, P, Sr, strontium, Ba, barium, Ca calcium, Mg, magnesium, Eu, europium, phosphor#, fluoresc?, phosphores?, lumin?